



Technical Data Sheet. Tribond 1130

Chemical Nature
Solids
Viscosity.
pH
Specific Gravity.

Copolymer Emulsion
Approx. 53%
Approx. 1500cps
Approx. 5
Approx. 1.04

DESCRIPTION.

Tribond 1130 is a very fast setting copolymer emulsion for use through jetting application equipment or via stereo rollers.. Tribond 1130 has a high tack and is clean running. Other properties include excellent heat and creep resistance, making it suitable for bonding some microwave susceptor patches. Tribond 1130 is suitable for bonding cellulosic and some lacquered surfaces. Customers are requested to check the adhesion performance before going in to full production. Bonds should be made and left 24 hours before assessment.

Users should evaluate the product to make sure all requirements are satisfied before going in to full production.

STORAGE.

Store at temperature above 7c to prevent damage by frost.
The storage life of this product is 3 months from date of manufacture.

HEALTH AND SAFETY.

None hazardous
Refer to the Material Safety Data Sheet for more information.

CAUTION.

This product has been manufactured to current quality and production specifications. Users of this product must carry out their own trials to ensure all requirements are satisfied. Trillium cannot guarantee the products suitability for the specific purpose of the customer due to the many factors that may affect storage, processing and application.