



Technical Data Sheet. Tribond 1155

Chemical Nature
Softening point °C
Viscosity @ 160°C
Specific Gravity.

EVA hot melt adhesive
Approx. 115
1000 cps
0.98

DESCRIPTION.

Tribond 1155 is a general purpose, low viscosity, fast setting packaging adhesive, designed with good high and low temperature resistance. This grade has been formulated to give a precise adhesive application and clean cut off at the nozzle.

Tribond 1155 exhibits high tack and a short open time. Recommended application temperature is 160°C to 180°C. This product is suitable for difficult substrates, but must be fully evaluated prior to production use.

STORAGE.

Store at temperature above 7°C to prevent damage by frost.
The storage life of this product is 12 months in un-opened packaging.

HEALTH AND SAFETY.

None hazardous in solid state.
Refer to the Material Safety Data Sheet for more information.

CAUTION.

This product has been manufactured to current quality and production specifications. Users of this product must carry out their own trials to ensure all requirements are satisfied. Trillium cannot guarantee the products suitability for the specific purpose of the customer due to the many factors that may affect storage, processing and application.