



## Technical Data Sheet. Tribond 1149

**Chemical Nature**  
**Softening point °C**  
**Viscosity @ 120°C**  
**Specific Gravity.**

**EVA hot melt adhesive**  
**Approx. 110**  
**1700 cps**  
**0.98**

### DESCRIPTION.

Tribond 1149 is a general purpose, low viscosity, fast setting packaging adhesive designed to be applied at low temperatures. This grade has been formulated to give a precise adhesive application and clean cut off at the nozzle.

Tribond 1149 exhibits high tack and a short open time. Recommended application temperature is 120°C to 150°C.

Users should evaluate the product to make sure all requirements are satisfied before going in to full production.

### STORAGE.

Store at temperature above 7°C to prevent damage by frost.  
The storage life of this product is 12 months in un-opened packaging.

### HEALTH AND SAFETY.

None hazardous in solid state.  
Refer to the Material Safety Data Sheet for more information.

### CAUTION.

This product has been manufactured to current quality and production specifications. Users of this product must carry out their own trials to ensure all requirements are satisfied. Trillium cannot guarantee the products suitability for the specific purpose of the customer due to the many factors that may affect storage, processing and application.