



## Technical Data Sheet. Tribond 1079

**Chemical Nature**  
**Solids**  
**Viscosity.**  
**pH**  
**Specific Gravity.**

**Vinyl Dextrin**  
**Approx. 64%**  
**Approx. 1100cps**  
**4-6**  
**Approx. 1.1**

### DESCRIPTION.

Tribond 1079 is a remoistenable coating/ adhesive suitable for bonding paper and board materials. Coatings can be applied and stored without blocking. By applying water the coating becomes reactivated to form bonds. Tribond 1079 has good heat resistance for use through laser printers without detriment to the coating. Typical applications are direct mailing; remoistenable front flap adhesive for envelopes and other high-speed applications, where glue lines can easily be washed off. Users should evaluate the product to make sure all requirements are satisfied before going in to full production.

### STORAGE.

Store at temperature above 7°C to prevent damage by frost.  
The storage life of this product is 3 months from date of manufacture.

### HEALTH AND SAFETY.

None hazardous  
Refer to the Material Safety Data Sheet for more information.

### CAUTION.

This product has been manufactured to current quality and production specifications. Users of this product must carry out their own trials to ensure all requirements are satisfied. Trillium cannot guarantee the products suitability for the specific purpose of the customer due to the many factors that may affect storage, processing and application.