



Technical Data Sheet. Tricote 1255

Chemical Nature
Solids
Viscosity.
pH
Specific Gravity.

Copolymer emulsion
Approx. 47%
Approx. 600cps
8.0 – 9.0
Approx. 1.02

DESCRIPTION.

Tricote 1255 has been developed for use as a barrier coating for paper and board, where water and grease resistance are required.

In static tests, Tricote 1255 provides a water barrier for over 1 week, with coatings of as little as 5 gsm* on Kraft paper.

Tricote 1255 complies with FDA 21 CFR 175.105, 176.170 and 176.180 with some limitations.

*Coat weight required will depend on the type of substrates used and application method.

Users should evaluate the product to make sure all requirements are satisfied before going in to full production.

STORAGE.

Store at temperature above 7°C to prevent damage by frost.

The storage life of this product is 3 months from date of manufacture.

HEALTH AND SAFETY.

None hazardous

Refer to the Material Safety Data Sheet for more information.

CAUTION.

This product has been manufactured to current quality and production specifications. Users of this product must carry out their own trials to ensure all requirements are satisfied. Trillium cannot guarantee the products suitability for the specific purpose of the customer due to the many factors that may affect storage, processing and application.